


# TARDEC




## Technical Report

No. 13620

### Compatibility of Single Hydraulic Fluid with Military Specification Fluids, Seals and Metallurgy

March 1995

By **Ellen M. Purdy**  
**Donna M. Rutkowski**  
USA Tank Automotive Command  
Mobility Technology Center Belvoir



19950405 019

istribution unlimited; approved for public release.

DTIC QUALITY INSPECTED 1



**U.S. Army Tank-Automotive Command**  
**Research, Development and Engineering Center**  
**Warren, Michigan 48397-5000**

The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

Citation of manufacturer's or trade names does not constitute an official endorsement or approval of the use thereof.

Destroy this report when it is no longer needed. Do not return it to the originator.

No. 13620

# Compatibility of Single Hydraulic Fluid with Military Specification Fluids, Seals and Metallurgy

March 1995

Accession For	
NTIS	CRA&I <input checked="" type="checkbox"/>
DTIC	TAB <input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By	
Distribution /	
Availability Codes	
Dist	Avail and / or Special
A-1	

By **Ellen M. Purdy**  
**Donna M. Rutkowski**  
USA Tank Automotive Command  
Mobility Technology Center Belvoir  
Fuels and Lubricants Division

# Contents

	Page
Section 1 Introduction and Background .....	1
Section 2 Technical Approach .....	3
Section 3 Results .....	4
Section 4 Conclusions.....	8
References.....	9

## Tables

1. Requirements for Desirable Military Hydraulic Fluids.....	1
2. Baseline Elastomer Compatibility.....	4
3. Sequential Elastomer Swell.....	5
4. Elastomer Swell of SHF Contaminated with FRH.....	6
5. Elastomer Swell of SHF Contaminated with OHT .....	6
6. Elastomer/Metallurgy Compatibility.....	7

## Section 1 Introduction and Background

The Army currently uses three military specification hydraulic fluids for its ground equipment; MIL-H-6083 (OHT); MIL-H-46170 (FRH); and MIL-H-5606 (OHA).<sup>1,2,3</sup> In The US Army currently relies on three different hydraulic fluids for its ground equipment. MIL-H-5606 (OHA) and MIL-H-6083 (OHT) are both petroleum base fluids with excellent low temperature operability, but poor fire resistance. MIL-H-46170 (FRH) is a synthetic hydrocarbon based hydraulic fluid with excellent fire resistance but poor low temperature performance.<sup>1,2,3</sup> Since none of the three fluids provide all desired characteristics for military purposes, the US Army Mobility Technology Center - Belvoir developed a modified fire resistant hydraulic fluid, designated Single Hydraulic Fluid (SHF), which exhibits satisfactory low temperature operability. This fluid has met all target performance requirements in the laboratory (see Table 1) and offers every indication of replacing the three currently used fluids.

**Table 1. Requirements for Desirable Military Hydraulic Fluid**

PERFORMANCE TEST	MIL-L-46170	SHF
Oxidation/Corrosion ASTM D4636, #3	168 hrs @ 121°C vis. < 10%	168 hrs @ 135°C vis. < 10%
Corrosion Inhibition ASTM D1748	100 hrs min	100 hrs min
Galvanic Corrosion FTM 5322	10 days min	10 days min
Low Temp Stability FTM 3458	72 hrs @ -54°C	72 hrs @ -54°C
Pour Point ASTM D97	-60°C min	-60°C min
Viscosity @ 40°C ASTM D445	19.5 cSt max	19.5 cSt max
Viscosity @ 100°C ASTM D445	3.4 cSt min	2.5 cSt min
Viscosity @ -40°C ASTM D445	2600 cSt max	800 cSt max
Viscosity @ -54°C ASTM D445	report	3500 cSt max
Solid particle Count MIL-H-46170	10,000 max @ 5-25 micrometers	10,000 max @ 5-15 micrometers
Solid Particle Count MIL-H-46170	250 max @ 26-50 micrometers	1,000 max @ 16-25 micrometers
Solid Particle Count MIL-H-46170	50 max @ 51-100 micrometers	150 max @ 26-50 micrometers
Solid Particle Count MIL-H-46170	10 max @ over 100 micrometers	20 max @ 51-100 micrometers

**Table 1. Requirements for Desirable Military Hydraulic Fluid (continued)**

PERFORMANCE TEST	MIL-L-46170	SHF
Solid Particle Count MIL-H-46170		5 max @ over 100 micrometers
Acid Number ASTM D664	0.2 gm KOH/gm max	0.3 gm KOH/gm max
Elastomer Swell FTM 3603	15% - 25%	19% - 28%
Evaporation Loss ASTM D972	5% max	35% max
Steel on Steel Wear ASTM D4172	0.3 mm max @ 10 kg load	0.3 mm max @ 10 kg load
Steel on Steel Wear ASTM D4172	0.65 mm max @ 40 kg load	0.65 mm max @ 40 kg load
Foam Characteristics ASTM D892	65 ml max	65 ml max
Water Content ASTM D1744	500 ppm max	100 ppm max
Flash Point ASTM D92	219°C min	180°C min
Fire Point ASTM D92	246°C min	190°C min
Autoignition Temp ASTM E659	343°C min	325°C min
Hi Temp/Hi Press Ignt FTM 6052	no continuation of burning when ignition source is removed	no continuation of burning when ignition source is removed
Flame Propagation MIL-H-83282	0.3 cm/sec max	0.3 cm/sec max
Storage Stability FTM 3465	12 months	12 months

To insure that the developmental SHF can successfully be fielded in Army ground equipment, compatibility with existing systems must be assured. Because SHF is intended as a one-to-one replacement for currently used fluids, it must be compatible not only with the metallurgy and elastomeric seals in the hydraulic systems but also with any residual hydraulic fluid that remains after conversion. To demonstrate this compatibility, SHF was subjected to varying amounts of fluid "contamination" with OHT and FRH, and tested in the presence of elastomeric materials and metals commonly used in hydraulic system components. OHA was not used as a test fluid as it is chemically identical to OHT except that it does not contain a corrosion inhibitor. IF SHF demonstrates compatibility with OHT it will be compatible with OHA.

## Section 2 Technical Approach

---

To demonstrate compatibility with existing fluids and seals, the investigation was conducted in three parts. First, all three fluids were subjected to elastomer swell testing with the elastomer samples of fluorosilicone (FVMC), polyurethane (AU), nitrile (NBR), polyacrylate (ACM), and fluorocarbon (CFM). The elastomers were tested for volume swell and hardness before and after a 168 hour soak in the test fluid at 70°C.<sup>4</sup> This established an initial baseline of performance for each fluid in the presence of the elastomers (see Table 2, page 4).

For the next phase, the elastomer samples from the FRH and OHT fluids were subjected to an additional 168 hour soak in SHF. Testing the elastomers in SHF after they have already been subjected to FRH or OHT provides an indication of how the seals in hydraulic systems will be affected after they have been changed over from FRH or OHT to SHF. This investigation is intended to determine if any excessive swelling, loss of volume swell, or deterioration occurs in the elastomers after they have experienced subsequent exposure to SHF. If no major changes in the elastomers occur upon exposure to SHF after previous exposure to OHT or FRH, fluid/elastomer compatibility will be partly established.

A final demonstration of fluid/elastomer compatibility involves treating SHF with varying concentrations of FRH and OHT. Samples of SHF were prepared that contained 1%, 3%, 5%, 10% and 15% FRH and OHT, thus a total of ten test fluids were subjected to the elastomer materials. Contaminating SHF with FRH and OHT simulates the conditions expected after a flush and fill conversion of a vehicle using FRH or OHT. If no excessive swelling, loss of volume swell, or deterioration of the elastomers occurs upon exposure to these mixed fluid samples, SHF will have truly demonstrated fluid and seal compatibility.

To demonstrate full compatibility with Army hydraulic systems, SHF was tested in the presence of both the elastomer materials and component metals. The metals used in testing were steel, cadmium, copper, magnesium, and aluminum. These metals are specified in FTM-791-5308, Corrosiveness and Oxidation Stability of Light Oils (Metal Squares).

## Section 3 Results

Baseline testing was accomplished by following FTM-791 Method #3603, Swelling of Synthetic Rubbers, for each of the test fluids. Table 2 summarizes the volume swell and seal hardness for each fluid and elastomer.

**Table 2. Baseline Elastomer Compatibility**

Seal	SHF			OHT			FRH		
	V%	HD <sub>i</sub>	HD <sub>f</sub>	V%	HD <sub>i</sub>	HD <sub>f</sub>	V%	HD <sub>i</sub>	HD <sub>f</sub>
FVMC	3.0	15	15	4.5	15	16	1.2	15	16
AU	1.0	22	22	1.2	22	22	0.6	22	23
NBR	3.0	20	19	6.1	20	19	1.5	20	21
ACM	3.3	18	16	5.8	18	17	1.7	18	17
CFM	0.7	26	25	0.7	25	22	0.6	26	22

**Key:** V% = Volume Swell  
 HD<sub>i</sub> = Initial Hardness  
 HD<sub>f</sub> = Final Hardness

As can be seen from the above data, OHT causes the seal materials to swell significantly more than FRH except for the fluorocarbon samples. OHT is also more proficient at seal swell than SHF for the test materials, although SHF provides more seal swell than FRH. For the fluorosilicone, polyurethane, and fluorocarbon materials, SHF provides sufficient seal swell to be comparable to OHT in performance even though SHF is slightly on the low side. The nitrile and polyacrylate materials, however, indicate a wider discrepancy between the OHT performance and SHF performance. It is not known if this discrepancy is significant enough to cause a difference in performance of the seals in actual vehicles. Table 2 also indicates the different effects the fluids have on seal hardness.

While the above baseline data allows some direct comparisons to be drawn from the fluids' effect on the elastomers, it does not give an indication of how SHF will perform in a vehicle that has been previously exposed to FRH or OHT. To pursue this question, sequential rubber swell tests were conducted. The same elastomer samples that yielded the above data were re-tested in SHF for an additional 168 hours. This type of sequential testing does not follow a standard test methodology in that submerging an elastomer previously subjected to an initial fluid in a second fluid has never been previously reported in literature. The same procedure for determining elastomer swell (FTM-791 Method #3603) was used on the already swelled elastomer sample, thus a logical methodology was utilized in obtaining this data. Table 3 provides the results of these subsequent exposures.



**Table 3. Sequential Elastomer Swell**

SEAL	SHF	OHT	OHT/SHF	FRH	FRH/SHF
FVMC	3.0%	4.5%	-16.8%	1.2%	-19.2%
AU	1.0%	1.2%	1.1%	0.6%	1.1%
NBR	3.0%	6.1%	3.9%	1.5%	3.9%
ACM	3.3%	5.8%	4.6%	1.7%	3.3%
CFM	0.7%	0.7	0.9%	0.6%	1.1%

**Key:** OHT/SHF = Final volume swell of elastomer sample after exposure to OHT then sequential exposure to SHF

FRH/SHF = Final volume swell of elastomer sample after exposure to FRH then sequential exposure to SHF

The data in Table 3 indicates the final state of the elastomer samples. By comparing columns 2, 3, and 4, it can be seen that except for the two fluoro elastomers, the subsequent immersion of the samples into SHF yielded a final swell which is greater than that achieved by SHF alone, yet less than what was originally exhibited after immersion in OHT. A comparison of columns 2, 5, and 6 indicates the situation is slightly different for the FRH/SHF samples. Except for the fluorosilicone, each elastomer sample exhibited seal swell equivalent to or greater than the swell achieved with SHF alone. The fluorocarbon samples exhibited a slight increase in swell for both OHT and FRH, but since the numbers are so close, it cannot actually be concluded that fluorocarbon increases in swell after subsequent exposure to SHF. The change in seal swell is not significant enough to be outside the "noise" of the test methodology. The results of the fluorosilicone test, however, are an anomaly. The test was repeated after the results indicated severe loss of seal swell, but the numbers were verified in the second test. This investigation has not pursued an explanation as to the chemistry between the fluids and fluorosilicone. At this time it can only be concluded that SHF is not compatible with a fluorosilicone seal that has previously been exposed to either FRH or OHT. If the fluorosilicone seal is brand new, it can be used with SHF with no risk of incompatibility or deterioration.

The next investigation into fluid/elastomer compatibility involved testing the SHF contaminated with varying concentrations of FRH and OHT. Tables 4 and 5 give the results of these tests. In addition to determining the volume swell of the elastomers, the mixed fluid viscosities, and flash and fire points were also determined.

**Table 4. Elastomer Swell of SHF Contaminated with FRH**

SEAL	SHF	1%FRH	3%FRH	5%FRH	10%FRH	15%FRH
FVMC	3.0%	2.6%	3.1%	2.6%	2.1%	2.2%
AU	1.0%	2.6%	1.4%	1.4%	1.0%	1.5%
NBR	3.0%	3.5%	3.6%	3.7%	3.1%	4.1%
ACM	3.3%	1.2%	3.1%	2.4%	2.2%	3.7%
CFM	0.7%	0.6%	0.2%	0.9%	0.3%	0.2%
VIS @ 40°C	10.2cSt	10.2cSt	10.4cSt	10.8cSt	10.9cSt	11.6cSt
VIS @ 100°C	2.8cSt	3.1cSt	3.0cSt	3.2cSt	3.2cSt	3.0cSt
Flash Point	184°C	186°C	186°C	188°C	188°C	190°C
Fire Point	202°C	196°C	196°C	204°C	204°C	206°C

Contamination of SHF with FRH from 1% to 15% results in little significant change in the elastomer swell. The addition of 15% FRH yields a change of only 1% increase in swell for the nitrile elastomer and a 1% decrease in swell for the fluorosilicone elastomer samples. This amount of FRH in SHF does have a some impact, however, on the fluid properties. Note from Table 4 that the flash point has increased to 190°C and the fire point has increased to 206°C. The viscosities remain relatively unaffected.

Addition of OHT to SHF also produced some minor effects. Volume swell for the nitrile sample showed a slight increase with the addition of OHT while the fluorocarbon exhibited a slight decrease. The most significant change occurred in the loss of fire and flash point. Addition of 15% OHT dropped the flash point to 156°C and the fire point to 170°C. Again, the viscosities remain relatively unchanged.

**Table 5. Elastomer Swell of SHF Contaminated with OHT**

SEAL	SHF	1%OHT	3%OHT	5%OHT	10%OHT	15%OHT
FVMC	3.0%	2.9%	2.6%	2.7%	2.8%	2.8%
AU	1.0%	1.4%	1.6%	1.4%	1.4%	1.4%
NBR	3.0%	4.3%	3.7%	3.8%	4.2%	3.6%
ACM	3.3%	2.9%	2.9%	3.3%	3.2%	3.3%
CFM	0.7%	0.8%	0.5%	0.5%	0.5%	0.5%
VIS @ 40°C	10.2cSt	10.5cSt	10.6cSt	10.6cSt	10.7cSt	11.2cSt
VIS @ 100°C	2.8cSt	3.4cSt	3.4cSt	3.5cSt	3.5cSt	3.8cSt
Flash Point	184°C	182°C	172°C	168°C	162°C	156°C
Fire Point	202°C	196°C	186°C	180°C	168°C	170°C

The final phase of this investigation involved testing the elastomer samples in the presence of metal coupons which are indicative of the metallurgy commonly used in Army hydraulic systems (see Table 6). The elastomers were tested for change in hardness (IRHD points) and volume swell, while the metal coupons were monitored for changes in weight ( $\text{mg}/\text{cm}^2$ ) and visual signs of corrosion. Weight changes of up to  $0.2\text{mg}/\text{cm}^2$  are acceptable for magnesium (Mg), aluminum (Al), iron (Fe), and cadmium (Cd), and up to  $0.6\text{ mg}/\text{cm}^2$  for copper (Cu). A change in hardness of +10 to -15 IRHD points is acceptable.

**Table 6. Elastomer/Metallurgy Compatibility**

Seal	$\Delta\text{VOL}\%$	$\Delta\text{HARD}$	$\Delta\text{Wt Cu}$	$\Delta\text{WT Mg}$	$\Delta\text{WT Al}$	$\Delta\text{WT Fe}$	$\Delta\text{WT Cd}$
FVMC	2.8%	-1	0.009	0.014	0.007	0.005	0.005
AU	0.1%	-2	0.014	0.011	0.008	0.020	0.006
NBR	2.4%	+9	0.001	0.012	0.022	0.012	0.018
ACM	2.5%	-1	0.006	0.015	0.027	0.005	0.046
CFM	1.9%	-1	0.001	0.007	0.002	0.001	0.003

As can be seen from Table 6, all coupon weight changes are well within acceptable limits, indicating no incompatibility of SHF with the metallurgy in the presence of different elastomers. The elastomer samples themselves exhibited no significant difference in volume swell in the presence of the metal coupons when compared to results obtained without the presence of coupons. Except for the nitrile, each elastomer sample only exhibited a change in hardness of 1 or 2 points. Referring back to Table 2, it can be seen that these changes in hardness are acceptable in that the baseline results for OHT and FRH are almost identical.

## Section 4. Conclusions

---

From this rather extensive compatibility study, it can be concluded that SHF is entirely compatible in all aspects with current Army hydraulic systems. SHF is completely miscible in OHT and FRH and remains stable in all temperature conditions.<sup>5</sup> Because no appreciable change in corrosion protection or elastomer swell occurs when SHF is combined with OHT or FRH in varying concentrations, hydraulic systems which contain SHF mixed with FRH or OHT can be expected to perform in a satisfactory manner.

Although no incompatibilities have been detected in this study, it is clear that for the sample elastomers investigated, SHF usually provides more seal swell than FRH and less seal swell than OHT. It cannot be determined conclusively that the amount of seal swell delivered by SHF is adequate for all seal materials in all Army vehicles. There still remains the possibility that SHF will cause seals designed for vehicles using FRH to swell too much and seals designed for vehicles using OHT to swell too little. This likelihood is remote, however, based on vehicles currently fielded. Both the M109 Self Propelled Howitzer and the M1A1 Battle Tank make extensive use of nitrile and fluorocarbon seals in their hydraulic systems.<sup>6,7</sup> The M109 utilizes OHT while the M1A1 uses FRH.<sup>8,9</sup> Neither vehicle exhibits problems with either seal leakage or sticking due to too much swell. Since FRH provides sufficient seal swell to prevent leakage and OHT does not cause seals to stick from excessive swelling, it can be concluded that SHF provides adequate seal swell which is neither too excessive or minimal.

## References

---

1. MIL-H-5606F, *Hydraulic Fluid, Petroleum Base*, 21 August 1991.
2. MIL-H-6083E, *Hydraulic Fluid, Petroleum Base for Preservation and Operation*, 15 November 1993.
3. MIL-H-46170B, *Hydraulic Fluid, Rust Inhibited, Fire Resistant, Synthetic Hydrocarbon Base*, 24 March 1986.
4. Federal Test Standard 791, Method 3603.5, *Swelling of Synthetic Rubbers*, 30 September 1986.
5. Purdy, Ellen M., "Development of a Single Hydraulic Fluid for Use in Army Ground Equipment", USA-BRDEC-TR//2540, October 1993.
6. TM 9-2350-01-311-24P-2, *Technical Manual for Direct Support and General Support Maintenance Repair and Special Tools List (Including Depot Maintenance Repair Parts and Special Tools) for Cab Armament, Sighting and Fire Control, Elevating and Transversing 155MM, M109A29(NSN 2350-01-301-0586)(EIC: 3EZ), M109A3(NSN 2350-01-0301-8851)(EIC: 3E2), M109A4(NSN 2350-01-277-5770)(EIC: 3E8), M109A5(NSN 2350-01-281-1719)(EIC: 3E7)*, December 11, 1991.
7. TM 9-2350-264-24P-2, *Technical Manual for Unit, Direct Support and General Support Maintenance Repair Parts and Special Tools List (Including Depot Maintenance Repair Parts) for Tank Combat, Full-Track: 120-MM Gun, M1A1(2350-01-087-1095) General Abrams, Turret*, November 1, 1993.
8. LO 9-2350-311-12, *Lube Order for Howitzer, Medium, Self-Propelled: 155MM, M109A2(2350-01-301-0586), M109A3(2350-01-0301-8851)*, May 13, 1985.
9. LO 9-2350-0252-12, *Lube Order for Tank, Combat, Full-Track, 105MM, M1 General Abrams(2350-01-061-2445)*, February 13, 1991.

# Distribution for TARDEC Technical Report 13620

## DEPARTMENT OF THE ARMY

HQDA  
1 ATTN DALO TSE  
1 ATTN DALO SM  
PENTAGON  
WASHINGTON DC 20310-0103

CDR AMC  
1 ATTN AMCRD S  
1 ATTN AMCRD E  
1 ATTN AMCRD IM  
1 ATTN AMCRD IT  
1 ATTN AMCRDA  
1 ATTN AMCRD MS  
1 ATTN AMCRD MT  
1 ATTN AMCICP ISI  
5001 EISENHOWER AVE  
ALEXANDRIA VA 22333-0001

TARDEC  
1 ATTN AMSTA CMA  
1 ATTN AMSTA CMB  
1 ATTN AMSTA CME  
1 ATTN AMSTA N  
1 ATTN AMSTA R  
1 ATTN AMSTA RG  
1 ATTN AMCPM ATP  
1 ATTN AMSTA Q  
1 ATTN AMSTA UE  
1 ATTN AMSTA UG  
CDR TACOM  
WARREN MI 48397-5000

CDR ARMY TACOM  
1 ATTN AMSTA FP  
1 ATTN AMSTA KL  
1 ATTN AMSTA MM  
1 ATTN AMSTA MT  
1 ATTN AMSTA MC  
1 ATTN AMSTA GT  
1 ATTN AMSTA FNG  
1 ATTN AMSTA FR  
1 ATTN USMC LNO  
1 ATTN AMSPM LAV  
1 ATTN AMSPM 113/M60  
1 ATTN AMCPM CCE/SMHE  
WARREN MI 48397-5000

TARDEC  
20 ATTN AMSTA-RBF  
CDR TACOM  
10101 GRIDLEY RD STE 128  
FT BELVOIR, VA 22060-5843

PROG EXEC OFFICER  
ARMORED SYS MODERNIZATION  
1 ATTN SFAE ASM S  
1 ATTN SFAE ASM BV  
1 ATTN SFAE ASM CV  
1 ATTN SFAE ASM AG  
CDR TACOM  
WARREN MI 48397-5000

PROG EXEC OFFICER  
ARMORED SYS MODERNIZATION  
1 ATTN SFAE ASM FR  
1 ATTN SFAE ASM AF  
PICATINNY ARSENAL  
NJ 07806-5000

PROG EXEC OFFICER  
COMBAT SUPPORT  
1 ATTN SFAE CS TVL  
1 ATTN SFAE CS TVM  
1 ATTN SFAE CS TVH  
CDR TACOM  
WARREN MI 48397-5000

PROG EXEC OFFICER  
ARMAMENTS  
1 ATTN SFAE AR HIP  
1 ATTN SFAE AR TMA  
1 PICATINNY ARSENAL  
NJ 07806-5000

PROJ MGR  
UNMANNED GROUND VEH  
1 ATTN AMCPM UG  
REDSTONE ARSENAL  
AL 35898-8060

DIR  
ARMY RSCH LAB  
1 ATTN AMSRL CP PW  
2800 POWDER MILL RD  
ADELPHIA MD 20783-1145

VEHICLE PROPULSION DIR  
1 ATTN AMSRL VP (MS 77 12)  
NASA LEWIS RSCH CTR  
21000 BROOKPARK RD  
CLEVELAND OH 44135

CDR AMSAA  
1 ATTN AMXSY CM  
1 ATTN AMXSY L  
APG MD 21005-5071

1 CDR ARO  
 1 ATTN AMXRO EN (D MANN)  
 RSCH TRIANGLE PK  
 NC 27709-2211  
  
 DIR  
 1 AMC PKG STO CONT CTR  
 1 ATTN SDSTO TE S  
 TOBYHANNA PA 18466-5097  
  
 CDR AEC  
 1 ATTN SFIM AEC ECC (T ECCLES)  
 APG MD 21010-5401  
  
 CDR ARMY ATCOM  
 1 ATTN AMSAT I ME (L HEPLER)  
 1 ATTN AMSAT I LA (V SALISBURY)  
 1 ATTN AMSAT R EP (V EDWARD)  
 4300 GOODFELLOW BLVD  
 ST LOUIS MO 63120-1798  
  
 CDR AVIA APPL TECH DIR  
 1 ATTN AMSAT R TP (H MORROW)  
 FT EUSTIS VA 23604-5577  
  
 CDR ARMY NRDEC  
 1 ATTN SATNC US (SIEGEL)  
 1 ATTN SATNC UE  
 NATICK MA 01760-5018  
  
 CDR ARMY ARDEC  
 1 ATTN SMCAR CC  
 1 ATTN SMCAR ESC S  
 PICATINNY ARSENAL  
 NJ 07808-5000  
  
 CDR ARMY CRDEC  
 1 ATTN SMCCR RS  
 APG MD 21010-5423  
  
 CDR ARMY DESCOM  
 1 ATTN AMSDS MN  
 1 ATTN AMSDS EN  
 CHAMBERSBURG PA 17201-4170  
  
 CDR ARMY AMCCOM  
 1 ATTN AMSMC MA  
 ROCK ISLAND IL 61299-6000  
  
 CDR ARMY WATERVLIET ARSN  
 1 ATTN SARWY RDD  
 WATERVLIET NY 12189  
  
 DIR AMC LOG SPT ACT  
 1 ATTN AMXLS LA  
 REDSTONE ARSENAL  
 AL 35890-7466  
  
 CDR APC  
 1 ATTN SATPC Q  
 1 ATTN SATPC QE (BLDG 85 3)  
 NEW CUMBERLAND  
 PA 17070-5005

1 PETROL TEST FAC WEST  
 BLDG 247 TRACEY LOC  
 DDRW  
 P O BOX 96001  
 STOCKTON CA 95296-960  
  
 CDR ARMY LEA  
 1 ATTN LOEA PL  
 NEW CUMBERLAND  
 PA 17070-5007  
  
 CDR ARMY TECOM  
 1 ATTN AMSTE TA R  
 1 ATTN AMSTE TC D  
 1 ATTN AMSTE EQ  
 APG MD 21005-5006  
  
 PROJ MGR PETROL WATER LOG  
 1 ATTN AMCPM PWL  
 4300 GOODFELLOW BLVD  
 ST LOUIS MO 63120-1798  
  
 PROJ MGM MOBILE ELEC PWR  
 1 ATTN AMCPM MEP  
 7798 CISSNA RD STE 200  
 SPRINGFIELD VA 22150-3199  
  
 CDR  
 ARMY COLD REGION TEST CTR  
 1 ATTN STECR TM  
 1 ATTN STECR LG  
 APO AP 96508-7850  
  
 CDR  
 ARMY BIOMED RSCH DEV LAB  
 1 ATTN SGRD UBZ A  
 FT DETRICK MD 21702-5010  
  
 CDR FORSCOM  
 1 ATTN AFLG TRS  
 FT MCPHERSON GA 30330-6000  
  
 CDR TRADOC  
 1 ATTN ATCD SL 5  
 INGALLS RD BLDG 163  
 FT MONROE VA 23651-5194  
  
 CDR ARMY ARMOR CTR  
 1 ATTN ATSB CD ML  
 1 ATTN ATSB TSM T  
 FT KNOX KY 40121-5000  
  
 CDR ARMY QM SCHOOL  
 1 ATTN ATSM CD  
 1 ATTN ATSM PWD  
 FT LEE VA 23001-5000  
  
 CDR  
 ARMY COMBINED ARMS SPT CMD  
 1 ATTN ATCL CD  
 1 ATTN ATCL MS  
 FT LEE VA 23801-6000

1 CDR ARMY FIELD ARTY SCH  
 1 ATTN ATSF CD  
 FT SILL OK 73503  
  
 CDR ARMY TRANS SCHOOL  
 1 ATTN ATSP CD MS  
 FT EUSTIS VA 23604-5000  
  
 CDR ARMY INF SCHOOL  
 1 ATTN ATSH CD  
 1 ATTN ATSH AT  
 FT BENNING GA 31905-5000  
  
 CDR ARMY AVIA CTR  
 1 ATTN ATZQ DOL M  
 1 ATTN ATZQ DI  
 FT RUCKER AL 36362-5115  
  
 CDR ARMY CACDA  
 1 ATTN ATZL CD  
 FT LEAVENWORTH KA 66027-5300  
  
 CDR ARMY ENGR SCHOOL  
 1 ATTN ATSE CD  
 FT LEONARD WOOD  
 MO 65473-5000  
  
 CDR ARMY ORDN CTR  
 1 ATTN ATSL CD CS  
 APG MD 21005  
  
 CDR ARMY SAFETY CTR  
 1 ATTN CSSC PMG  
 1 ATTN CSSD SPS  
 FT RUCKER AL 36362-5363  
  
 CDR ARMY CSTA  
 1 ATTN STECS EN  
 1 ATTN STECS LI  
 1 ATTN STECS AE  
 1 ATTN STECS AA  
 APG MD 21005-5059  
  
 CDR ARMY YPG  
 1 ATTN STEYP MT TL M  
 YUMA AZ 85365-9130  
  
 CDR ARMY CERL  
 1 ATTN CECER EN  
 P O BOX 9005  
 CHAMPAIGN IL 61826-9005  
  
 1 DIR  
 AMC FAST PROGRAM  
 10101 GRIDLEY RD STE 104  
 FT BELVOIR VA 22060-5818  
  
 CDR I CORPS AND FT LEWIS  
 1 ATTN AFZH CSS  
 FT LEWIS WA 98433-5000

CDR  
 RED RIVER ARMY DEPOT  
 1 ATTN SDSRR M  
 1 ATTN SDSRR Q  
 TEXARKANA TX 75501-5000

PS MAGAZINE DIV  
 1 ATTN AMXLS PS  
 DIR LOGSA  
 REDSTONE ARSENAL  
 AL 35898-7466

CDR 6TH ID (L)  
 1 ATTN APUR LG M  
 1060 GAFFNEY RD  
 FT WAINWRIGHT  
 AK 99703

#### DEPARTMENT OF THE NAVY

OFC OF NAVAL RSCH  
 1 ATTN ONR 464  
 800 N QUINCY ST  
 ARLINGTON VA 22217-5660

CDR  
 NAVAL SEA SYSTEMS CMD  
 1 ATTN SEA 03M3  
 2531 JEFFERSON DAVIS HWY  
 ARLINGTON VA 22242-5160

CDR  
 NAVAL SURFACE WARFARE CTR  
 1 ATTN CODE 632  
 1 ATTN CODE 859  
 3A LEGGETT CIRCLE  
 ANNAPOLIS MD 21401-5067

CDR  
 NAVAL RSCH LABORATORY  
 1 ATTN CODE 6181  
 WASHINGTON DC 20375-5342

CDR  
 NAVAL AIR WARFARE CTR  
 1 ATTN CODE PE33 AJD  
 P O BOX 7176  
 TRENTON NJ 08628-0176

1 CDR  
 NAVAL PETROLEUM OFFICE  
 CAMERON STA T 40  
 5010 DUKE STREET  
 ALEXANDRIA VA 22304-6180

1 OFC ASST SEC NAVY (I 7 E)  
 CRYSTAL PLAZA 5  
 2211 JEFFERSON DAVIS HWY  
 ARLINGTON VA 22244-5110



CDR

NAVAL AIR SYSTEMS CMD  
1 ATTN AIR 53623C  
1421 JEFFERSON DAVIS HWY  
ARLINGTON VA 22243-5360

**DEPARTMENT OF THE NAVY  
U.S. MARINE CORPS**

HQ USMC

1 ATTN LPP  
WASHINGTON DC 20380-0001

1 PROG MGR COMBAT SER SPT  
MARINE CORPS SYS CMD  
2033 BARNETT AVE STE 315  
QUANTICO VA 22134-5080

1 PROG MGR GROUND WEAPONS  
MARINE CORPS SYS CMD  
2033 BARNETT AVE

QUANTICO VA 22134-5080

1 PROG MGR ENGR SYS  
MARINE CORPS SYS CMD  
2033 BARNETT AVE  
QUANTICO VA 22134-5080

CDR

MARINE CORPS SYS CMD  
1 ATTN SSE  
2033 BARNETT AVE STE 315  
QUANTICO VA 22134-5010

CDR

BLOUNT ISLAND CMD  
1 ATTN CODE 922/1  
814 RADFORD BLVD  
JACKSONVILLE  
FLA 32226-3404

CDR

MARINE CORPS LOGISTICS BA  
1 ATTN CODE 837  
814 RADFORD BLVD  
ALBANY GA 31704-1128

1 CDR  
2ND MARINE DIV  
PSC BOX 20090  
CAMP LEJEUNE  
NC 28542-0090

1 CDR  
1ST MARINE DIV  
CAMP PENDLETON  
CA 92055-5702

1 CDR  
FMFPAC G4  
BOX 64118  
CAMP H M SMITH  
HI 96861-4118

**DEPARTMENT OF DEFENSE**

ODUSD

1 ATTN (L) MRM  
PETROLEUM STAFF ANALYST  
PENTAGON  
WASHINGTON DC 20301-8000

ODUSD

1 ATTN (ES) CI  
400 ARMY NAVY DR  
STE 206  
ARLINGTON VA 22202

HQ USEUCOM

1 ATTN ECJU L1J  
UNIT 30400 BOX 1000  
APO AE 09128-4209

US CINCPAC

1 ATTN J422 BOX 64020  
CAMP H M SMITH  
HI 96861-4020

1 JOAP TSC

BLDG 780  
NAVAL AIR STA  
PENSACOLA FL 32408-5300

DIR DLA

1 ATTN DLA MMDI  
ATTN DLA MMSB  
CAMERON STA  
ALEXANDRIA VA 22304-6100

CDR

DEFENSE FUEL SUPPLY CTR  
1 ATTN DFSC Q BLDG 8  
1 ATTN DFSC S BLDG 8  
CAMERON STA  
ALEXANDRIA VA 22304-6160

CDR

DEFENSE GEN SUPPLY CTR  
1 ATTN DGSC SSA  
1 ATTN DGSC STA  
8000 JEFFERSON DAVIS HWY  
RICHMOND VA 23297-5678

DIR ADV RSCH PROJ AGENCY

1 ATTN ARPA/ASTO  
3701 N FAIRFAX DR  
ARLINGTON VA 22203-1714

12 DEFENSE TECH INFO CTR  
CAMERON STATION  
ALEXANDRIA VA 22314

**DEPARTMENT OF AIR FORCE**

HQ USAF/LGSSF

1 ATTN FUELS POLICY  
1030 AIR FORCE PENTAGON  
WASHINGTON DC 20330-1030

1 HQ USAF/LGTV  
ATTN VEH EQUIP/FACILITY  
1030 AIR FORCE PENTAGON  
WASHINGTON DC 20330-1030

AIR FORCE WRIGHT LAB  
1 ATTN WL/POS  
1 ATTN WL/POSF  
1 ATTN WL/POSL  
1790 LOOP RD N  
WRIGHT PATTERSON AFB  
OH 45433-7103

AIR FORCE WRIGHT LAB  
1 ATTN WL/MLBT  
2941 P ST STE 1  
WRIGHT PATTERSON AFB  
OH 45433-7750

AIR FORCE WRIGHT LAB  
1 ATTN WL/MLSE  
2179 12TH ST STE 1  
WRIGHT PATTERSON AFB  
OH 45433-7718

1 AIR FORCE MEEP MGMT OFC  
615 SMSQ/LGTV MEEP  
201 BISCAYNE DR STE 2  
ENGLIN AFB FL 32542-5303

1 SA ALC/SFT  
1014 ANDREWS RD STE 1  
KELLY AFB TX 78241-5603

1 WR ALC/LVRS  
225 OCMULGEE CT  
ROBINS AFB  
GA 31098-1647